Fabric: Type: Fog - Projection Screen BS5867 Part 2 Type B





Wira House, West Park Ring Road, Leeds, LS16 6QL, UK. Telephone: +44 (0)113 259 1999 Email: <u>info@bttg.co.uk</u> Website: <u>www.bttg.co.uk</u>

Date:

01 September 2017

Our Ref: Your Ref: 53939-3

Page:

1 of 4

Client:

J. & C. Joel Limited Corporation Mill Corporation Street Sowerby Bridge Halifax HX6 2QQ

Job Title:

Surface Ignition Of Curtains & Drapes

Client's Order No:

Date of Receipt: Date of Test Start: 21 August 2017 01 September 2017

Description of Sample(s):

One sample identified as follows was received for testing:

PVC Projection Screen, stated to be DFR

Work Requested:

We were asked to make the following test:

BS 5867: Part 2: 2008 (2015): Type B Curtains, Drapes and Blinds



Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, L516 6QL.
A company registered in England & Wales with company number 04669551. VAT Number GB 816764800.
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2017 Shirley Technologies Limited. All rights reserved.

Fabric: Fog - Projection Screen **Type:** BS5867 Part 2 Type B





Wira House, West Park Ring Road, Leeds, LS16 6QL, UK. Telephone: +44 (0)113 259 1999 Email: <u>info@bttg.co.uk</u> Website: <u>www.bttg.co.uk</u>

Date:

01 September 2017

Our Ref: Your Ref: 53939-3

Page:

2 of 4

J. & C. Joel Limited

Sample was identified as follows:

PVC Projection Screen, stated to be DFR

BS 5867: Part 2: 2008 (2015): Type B Curtains, Drapes and Blinds

Three specimens from both length and width were tested in accordance with BS EN ISO 15025: Procedure A (surface ignition): 2002. The sample was tested at 20 °C and 60 % relative humidity (R.H.).

Each specimen was subjected to an applied flame using propane and a 15 second flame application time. The results obtained (shown in the table below) were assessed according to the requirements of BS 5867: Part 2: 2008 (2015).

Pre-treatment

If the fabric is a <u>pass</u> in the 'as received' condition then the fabric is subjected a water soak procedure as specified in BS EN 1021: Annex D: 2006.

Testing after pre-treatment

Three specimens, after pre-treatment, from both length and width were tested following the procedure described above.

Test results relate only to the sample tested.

The results for all tests are given in the table(s) on the following page(s).

Reported by:....
J Coleman
Fire Technician

.. Countersigned By:.

Operational Head

Enquiries concerning this report should be addressed to Customer Services.



Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2017 Shirley Technologies Limited. All rights reserved

Fabric: Type:

Fog - Projection Screen BS5867 Part 2 Type B





Wira House, West Park Ring Road, Leeds, LS16 6QL, UK. Telephone: +44 (0)113 259 1999 Email: info@bttg.co.uk Website: www.bttg.co.uk

Date:

01 September 2017

Our Ref: Your Ref: 53939-3

Page:

3 of 4

J. & C. Joel Limited

RESULTS

Sample Ref:

PVC Projection Screen, stated to be DFR

BS 5867: Part 2: 2008 (2015): Type B Curtains, Drapes and Blinds

| Specimen No. | Length | | | Width | | |
|--------------------------|--------|----|----|-------|----|----|
| | 1 | 2 | 3 | 4 | 5 | 6 |
| Flame reached an edge | No | No | No | No | No | No |
| Hole reached an edge | No | No | No | No | No | No |
| Flaming debris separated | No | No | No | No | No | No |

Any "Yes" means fail except if only one specimen fails a further 6 specimens are tested, if the second 6 specimens all pass the result is a pass.

Result in 'as received': Pass

Testing after pre-treatment

| Specimen No. | Length | | | Width | | |
|--------------------------|--------|----|----|-------|----|----|
| | 1 | 2 | 3 | 4 | 5 | 6 |
| Flame reached an edge | No | No | No | No | No | No |
| Hole reached an edge | No | No | No | No | No | No |
| Flaming debris separated | No | No | No | No | No | No |

Any "Yes" means fail except if only one specimen fails a further 6 specimens are tested, if the second 6 specimens all pass the result is a pass.

Result in 'after pre-treatment': Pass





Shirley* Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, L516 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2017 Shirley Technologies Limited. All rights reserved.

Fabric: Type: Fog - Projection Screen BS5867 Part 2 Type B





Wira House, West Park Ring Road, Leeds, LS16 6QL, UK. Telephone: +44 (0)113 259 1999 Email: <u>info@bttg.co.uk</u> Website: <u>www.bttg.co.uk</u>

Date: 01 September 2017

Our Ref: 53939-3 Your Ref: -

Page: 4 of 4

J. & C. Joel Limited

Conclusion

The fabric meets the Type B performance requirements of BS 5867: Part 2: 2008 (2015).

This material should be identified with the manufacturers name, trademark or other identifying mark, the statement 'Flammability complies with the requirements of BS 5867: Part 2: Type B and instructions of any special precautions to be taken concerning care (including cleansing) of the curtain, drape or window blind to be manufactured from the fabric, preferably using an appropriate care labelling symbol in accordance with BS EN 23758 and taking account of the pre-treatment using in this test and the requirements of Clause 4 of BS 5867: Part 2: 2008 (2015). If the fabric is unsuitable for cleansing, this shall be stated.

Uncertainty Budget

There is no uncertainty budget associated with BS 5867: Part 2: Type B as no measurements are determined, the pass/fail criteria is assessed visually.





Shirley* Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, L516 6QL.
A company registered in England & Wales with company number 0466951. VAT Number GB 816764800.
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2017 Shirley Technologies Limited. All rights reserved.