Fire Test Certificate - Specimen

Fabric: Mercury
Type: B1

J&C Joel
Inspiration in every performance

Prüfinstitut Hoch GmbH
Lerchenweg 1
D-97650 Fladungen
Tel.: int – 49 – 9778-7480-200
hoch.fladungen@t-online.de www.reaction-to-fire.de

Hoch Fladungen

Test laboratory for the fire behavior of building materials
Testing, supervising and certifying body, authorized by the building supervision authority

TEST REPORT
PZ-Hoch-251400

for the proof of Fire behaviour according to DIN 4102, part 1
Translation of the German test report – no guarantee for translation of technical terms

SPECIMEN

description of samples	3-layer fabric consisting of 100% Polyester FR colour. beige
name of the material	**„6904 6905 Venus"**
sampling	by the company itself
content of request	Proof of flammability to classify building materials to class B1 "schwerentflammbar" according to DIN 4102, part 1
validity of test report	31.10.2030
result	**The examined product meets the requirements of class B1 for "schwerentflammbare" (hardly flammable) building materials according to DIN 4102, part 1 (May 1998), suspended freely or with distance of >40 mm to same or other plain materials.**

This test report includes 4 pages and 3 enclosures.

Remark: If the above mentioned building material is not used as product according to MBO § 2, Abs. 9, Ziffer1, there is no need for a general building supervisory test report.
This test report is not valid if the examined building material is used as product in the meaning of state building prescriptions (MBO § 17, Abs. 3).
This test report does not replace an eventually necessary proof of applicability concerning building supervisory or building laws in the meaning of state building prescriptions. This has to be verified by:

- "allgemeine bauaufsichtliche Zulassung" (general building inspectorate approval) or by
- „allgemeines bauaufsichtliches Prüfzeugnis" (general building inspectorate certificate) or by
- "Zustimmung im Einzelfall" (exceptional approval)

This test report can underlie building supervisory procedures

- for regular building products for the prescribed proofs of conformity
- for non-regular building products for the needed proofs of applicability.

This test report must not be published and copied without preceding agreement of the test laboratory and if agreed, only during validity and unchanged concerning appearance and contents.

member of egolf
notified body no.: 1508

By the DAkkS according to DIN EN ISO/IEC 17025 accredited test laboratory.
The accreditation is valid for the testing methods specified in the certificate.

DAkkS Deutsche Akkreditierungsstelle D-PL-11005-01-00

United Kingdom
+44 1422 833835
uksales@jcjoel.com

United Arab Emirates
+971 4 884 7801
menasales@jcjoel.com

www.jcjoel.com

Hoch Fladungen
Prüfinstitut Hoch GmbH
Lerchenweg 1
D-97650 Fladungen

1. Description of test material in condition as delivered

PN 42756: „6904 6905 Venus" colour: beige

- 3-layer fabric consisting of 100% Polyester FR -

The inner layer is black.

There is no difference between side A and side B.

characteristic values determined by the test laboratory:

area weight: about 244g/m² thickness: about 0,45mm

The testing laboratory is not provided with further details concerning composition of the tested building materials. Samples are deposited.

2. Preparation of samples

The samples were kept in climate chamber 23/50 until they reached constant weight.

3. Arrangement of samples

mounting: freely suspended

#1014: flaming side B in weft direction
#1015: flaming side A in warp direction

4. Date of test

CW 45 in 2025

5. Results

The test has been examined according to DIN 4102 (Mai 1998)

line no.	Measurement	Result with the tested specimen				Dim.
	Test number	#1014	#1015	---	---	
	flaming direction / side	weft / B	warp / A	---	---	
1	Number of specimen arrangement acc. to. DIN 4102/T15, schedule 1	1	1	---	---	
2	Maximum flame height above bottom edge of the specimen	30	30			cm
3	Time [1]	0:04	0:04	---	---	min:s
4	Burn through / melting Time [1]	0:04	0:04	---	---	min:s
	Observations on the back side of the specimen					
	Flames / Glowing	---	---	./.	./.	
5	Time [1]	./.	./.	./.	./.	min:s
	Change of colour	---	---	./.	./.	
6	Time [1]	./.	./.	./.	./.	min:s
	Falling of burning droplets	./.	./.	./.	./.	
7	Start [1]	./.	./.	./.	./.	min:s
	Extent					
8	sporadic falling of burning droplets [2]	./.	./.	./.	./.	
9	continuous falling of burning droplets [2]	./.	./.	./.	./.	min:s
	Falling of burning droplets	./.	./.	./.	./.	
10	Start [1]					min:s
	Extent	./.	./.	./.	./.	
11	sporadic falling of burning droplets [2]					
12	continuous falling of burning droplets [2]	./.	./.	./.	./.	
13	After flame time at the bottom of the sieve (max.)	./.	./.	./.	./.	min:s

SPECIMEN

Fire Test Certificate - Specimen

Fabric: Mercury
Type: B1

J&C Joel
Inspiration in every performance

Hoch Fladungen
Prüfinstitut Hoch GmbH
Lerchenweg 1
D-97650 Fladungen

line no	Measurement	Result with the tested specimen				Dim.
	Test number	#1014	#1015	---	---	
	flaming direction / side	weft / B	warp / A	---	---	
14	Impairment of the burner by dropping or falling material: Time [1]	./.	./.	./.	./.	min:s
15	Final occurance of burning at the specimen [1]	./.	./.	./.	./.	min:s
16	Time of eventually end of test [1]	./.	./.	./.	./.	min:s
	After flame after end of test					
17	Time [1]	./.	./.	./.	./.	min:s
18	Number of specimen	./.	./.	./.	./.	
19	Front side of specimen [2]	./.	./.	./.	./.	
20	Back side of specimen [2]	./.	./.	./.	./.	
21	flame length	./.	./.	./.	./.	cm
	Afterglow after end of test	./.	./.	./.	./.	
22	Time [1]	./.	./.	./.	./.	min:s
23	Number of specimen	./.	./.	./.	./.	
	Place of appearance	./.	./.	./.	./.	
24	Lower half of the specimen [2]	./.	./.	./.	./.	
25	Upper half of the specimen [2]	./.	./.	./.	./.	
26	Front side of specimen [2]	./.	./.	./.	./.	
27	Back side of specimen [2]	./.	./.	./.	./.	
	Density of smoke					
28	≤ 400 % * min	1	1	---	---	% * min
29	> 400 % * min [4]	./.	./.	./.	./.	% * min
30	Diagram: encl. no.	1	2	---	---	
	Residual lengths: individual value [3]					
31	Specimen 1	60	56	---	---	cm
	Specimen 2	58	58	---	---	cm
	Specimen 3	56	66	---	---	cm
	Specimen 4	66	67	---	---	cm
32	Average value, individual test [3]	**60**	**62**	**---**	**---**	
33	Photo of specimen in enclosure no.	1	2	---	---	
34	Flue gas temperature	109	107	---	---	°C
35	Maximum of average value Time [1]	09:52	09:57	---	---	min:s
36	Diagram: encl. no.	1	2	---	---	
37	Remarks: - none -					

[1] indication of times: from the begin of testing procedure [2] checked off if applicable
[3] indication of carrier/foam layer separated in case of fire-proofing agents
[4] very strong development of smoke

SPECIMEN

United Kingdom
+44 1422 833835
uksales@jcjoel.com

United Arab Emirates
+971 4 884 7801
menasales@jcjoel.com

www.jcjoel.com

Prüfinstitut Hoch GmbH
Lerchenweg 1
D-97650 Fladungen

6. Explanations concerning the testing procedure

There were no additional tests proceeded because of the residual length of more than 45 cm.

7. Summary of results and additional establishments to Fire Behaviour

lineno.	measurement / test-no.	Result with the tested specimen				dimension
		#1014 weft / B	#1015 warp / A	---	---	
1	residual length	**60**	**62**	---	---	cm
2	max. smoke temperature	**109**	**107**	---	---	°C
3	density of smoke - integral	**1**	**1**	---	---	%min
4	remarks: -none-					

According to DIN 4102, part 1, "schwerentflammbare" (hardly flammable) building materials must meet the requirements of class B2.

Pursuant to additional tests in the ignitability apparatus this can be determined (appendix 3).

8. Special remarks

- This report is only valid for the material as described under paragraph 1. In combination with other materials or with additional coatings or grounds etc. the burning behaviour may differ.
- This test report is not valid for the exposure to outdoor climate conditions, washing or cleaning with chemicals.
- This test report is not valid, as soon as the fabric is used as a building product in the sense of the "Landesbauordnungen" (state building requirements, MBO § 17, par. 3).
- This test report is no substitute for a General Building Inspectorate Certificate.
- This test report is granted without prejudice to the rights of third parties, in particular private proprietary rights.
- For legal interests only the German original version is relevant.
- In General Building Inspectorates procedures this test report can be based for
  - regular building materials for the required proof of accordance
  - for not regular building materials for the required proof of applicability

9. Validity

This test report is valid until the mentioned date on page 1. The test report becomes invalid in case the standards on which the tests are based are changed.

Fladungen, 11.11.2025

clerk in charge:

(Dipl.-Ing. (FH) Jürgen Hammer)

ANERKANNTE PRÜF-, ÜBERWACHUNGS- UND ZERTIFIZIERUNGSSTELLE Hoch Fladungen

Head of the test laboratory:

(Dipl.-Ing.(FH) Andreas Hoch)

End of report

SPECIMEN

Fire Test Certificate - Specimen


Fabric: Mercury
Type: B1

J&C Joel
Inspiration in every performance

Hoch Fladungen
Prüfinstitut Hoch GmbH
Lerchenweg 1
D-97650 Fladungen


enclosure 1 test report
PZ-Hoch-251400

„Brandschacht"-test #1014



measurement

#1014, PN42756: B+S
Max. flue temperature: 109°C, Smoke density integral: 1%min
Residual length: 60 cm



SPECIMEN

United Kingdom
+44 1422 833835
uksales@jcjoel.com

United Arab Emirates
+971 4 884 7801
menasales@jcjoel.com

www.jcjoel.com

Fire Test Certificate - Specimen

Fabric: Mercury
Type: B1

J&C Joel
Inspiration in every performance

Hoch Fladungen

Prüfinstitut Hoch GmbH
Lerchenweg 1
D-97650 Fladungen

enclosure 2 test report
PZ-Hoch-251400


„Brandschacht"-test #1015



SPECIMEN

measurement

#1015, PN42756: A+K
Max. flue temperature: 107°C, Smoke density integral: 1%min
Residual length: 62 cm



United Kingdom
+44 1422 833835
uksales@jcjoel.com

United Arab Emirates
+971 4 884 7801
menasales@jcjoel.com

www.jcjoel.com

Fire Test Certificate - Specimen

Fabric: Mercury
Type: B1

J&C Joel
Inspiration in every performance

Prüfinstitut Hoch GmbH
Lerchenweg 1
D-97650 Fladungen

enclosure 3 to test report
PZ-Hoch-251400

Test for normal flammability
classifying B2 according to DIN 4102

1. Description of test material in condition as delivered look at page 2
2. Preparation of samples
   Out of the material there have been cut samples for the ignitability apparatus.
   The samples were kept in a climate 23/50 until they reached constant weight.
3. Arrangement of samples -freely suspended-
   Flaming in warp and weft direction / Flaming side A and side B
4. Date of test CW 44 in 2025
5. Results

PN 42756: flaming side A in warp	edge-test						surface-test						Dim
samples no.	1	2	3	4	5	6	1	2	3	4	5	6	
ignition[1]	1	1	1	1	1	--	2	--	--	--	--	--	s
reaching the mark of measurement[1)2)]	./.	./.	./.	./.	./.	--	./.	--	--	--	--	--	S
max. flame height	**5**	**6**	**5**	**7**	**5**	--	**4**	--	--	--	--	--	cm
time	6	4	4	7	4	--	7	--	--	--	--	--	
self cessation of the flames end of afterflame[1)]	10	5	8	10	5	--	10	--	--	--	--	--	s
end of glowing[1)]	./.	./.	./.	./.	./.	--	./.	--	--	--	--	--	s
flames were extinguished after[1)]	./.	./.	./.	./.	./.	--	./.	--	--	--	--	--	s
smoke development (visual)	little						little						
dropping of burning material during 20 s[1)]	./.	./.	./.	./.	./.	--	./.	--	--	--	--	--	s
Appearance after test: burned out till max. height 6cm x width 2cm													

PN 42756: additional tests	edge-test						surface-test						Dim
samples no.	1	2	3	4	5	6	1	2	3	4	5	6	
arrangement of samples side / direction	B/K	A/S	B/S	--	--	--	B/K	A/S	B/S	--	--	--	
ignition[1)]	1	1	1	--	--	--	2	2	2	--	--	--	s
reaching the mark of measurement[1)2)]	./.	./.	./.	--	--	--	./.	./.	./.	--	--	--	s
max. flame height	**5**	**5**	**3**	**--**	**--**	**--**	**5**	**3**	**4**	--	--	--	cm
time	4	3	4	--	--	--	5	3	5	--	--	--	
self cessation of the flames end of afterflame[1)]	5	4	4	--	--	--	8	4	8	--	--	--	s
end of glowing[1)]	./.	./.	./.	--	--	--	./.	./.	./.	--	--	--	s
flames were extinguished after[1)]	./.	./.	./.	--	--	--	./.	./.	./.	--	--	--	s
smoke development (visual)	little						little						
dropping of burning material during 20 s[1)]	./.	./.	./.	--	--	--	./.	./.	./.	--	--	--	s
Appearance after test: burned out till max. height 6 cm x width 2 cm													

[1)] time mentioned from the beginning of the test [2)] during 20 Sec -/- no appearance -- no information
K: warp / S: weft

6. Remarks and explanations to the testing procedure - none –
7. Opinion concerning the dropping of burning material
   The test for normal flammability shows no burning dripping material.

End of enclosures

P06-04-FB05 eng Rev01

SPECIMEN