Fire Test Certificate - Specimen

Fabric: Mercury
Type: NFPA 701

J&C Joel
Inspiration in every performance

DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE
"We Test Per Your Request"
336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

August 26, 2026

Reference: Laboratory Test Report
Lab Identification No. 69338
Invoice No. 100597

Dear Mr. Topen:

One (1) fabric sample, identified as **6904 6905 Venus,** was received and tested in accordance with the National Fire Protection Association No. 701, "Standard Methods of Fire Tests for Flame Propagation of Textiles and Films, 2023 Edition, (Test 2, Folds Configuration)". The results are as follows:

SPECIMEN

Test Results

Specimen Number	After Flame (sec)	Residual Flame (sec)	Char Length (in)
1	0.0	0.0	10.2
2	0.0	0.0	10.5
3	0.0	0.0	11.0
4	0.0	0.0	12.1

The fabric sample submitted **meets** the minimum requirements of the above standard. The length of char on the individual folded specimens shall not exceed 41.3 inches. Additionally, no specimen shall continue flaming for more than two (2) seconds after the test flame is removed and no residues shall fall to the floor of the test chamber and continue flaming for more than two (2) seconds at any time during the test.

Sincerely,

Brian S. Dement

DIVERSIFIED TESTING LABORATORIES, INC. SEAL 1975 NORTH CAROLINA

Brian S. Dement

BSD/mr

OUR LETTERS AND REPORTS ARE FOR THE EXCLUSIVE USE OF THE CLIENT TO WHOM THEY ARE ADDRESSED. ANY COMMUNICATION TO OTHERS OR THE USE OF OUR COMPANY NAME MUST RECEIVE PRIOR APPROVAL. OUR TEST RESULTS APPLY ONLY TO THE SAMPLE TESTED AND ARE NOT NECESSARILY INDICATIVE OF THE QUALITIES OF APPARENTLY IDENTICAL OR SIMILAR PRODUCTS. UNLESS OTHERWISE SPECIFIED, ALL COMPLIANCE STATEMENTS ARE SIMPLE ACCEPTANCE. SAMPLES NOT DESTROYED IN TESTING ARE RETAINED A MAXIMUM OF THIRTY DAYS. THE LETTERS, REPORTS OR NAME OF DIVERSIFIED TESTING LABORATORIES, INC. MAY NOT BE USED IN ADVERTISING TO THE GENERAL PUBLIC.