


Fire Test Certificate - Specimen

Fabric: Regal Satin (Double Sided)

Type: NFPA 70

J&C Joel 
Inspiration in every performance



DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

August 22, 2018

Reference: Laboratory Test Report
Lab Identification No. 31935
Invoice No. 63121

Dear Ms. Schmidt-Koch:

One (1) sample, identified as **ARTICLE GLAMOUR DIMOUT 33046**, was received and tested in accordance with the National Fire Protection Association No. 701, "Standard Methods of Fire Tests for Flame Propagation of Textiles and Films, 2015 Edition, (Test 1)". The results are as follows:

Specimen Number	Test Results	
	Residual Flame (seconds)	Weight Loss (percent)
1	0.0	18.35
2	0.0	21.99
3	0.0	21.67
4	0.0	22.00
5	0.0	12.66
6	0.0	26.97
7	0.0	22.15
8	0.0	21.46
9	0.0	7.56
<u>10</u>	<u>0.0</u>	<u>25.52</u>
AVG	0.0	20.03

The sample submitted **meets** the minimum requirements of the above standard. The average percent weight loss cannot exceed 40% and the weight loss of individual specimens cannot exceed mean value plus three standard deviations. The average residual flame cannot exceed 2.0 seconds.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr



OUR LETTERS AND REPORTS ARE FOR THE EXCLUSIVE USE OF THE CLIENT TO WHOM THEY ARE ADDRESSED. ANY COMMUNICATION TO OTHERS OR THE USE OF OUR COMPANY NAME MUST RECEIVE PRIOR APPROVAL. OUR TEST RESULTS APPLY ONLY TO THE SAMPLE TESTED AND ARE NOT NECESSARILY INDICATIVE OF THE QUALITIES OF APPARENTLY IDENTICAL OR SIMILAR PRODUCTS. SAMPLES NOT DESTROYED IN TESTING ARE RETAINED A MAXIMUM OF THIRTY DAYS. THE LETTERS, REPORTS OR NAME OF DIVERSIFIED TESTING LABORATORIES, INC. MAY NOT BE USED IN ADVERTISING TO THE GENERAL PUBLIC.