

Fire Test Certificate - Specimen

Fabric: Embrace

Type: IMO

J&C Joel 
Inspiration in every performance

intertek
Total Quality. Assured.

Intertek
The Warehouse
Brewery Lane
Leigh WN7 2RJ
UK

Tel +44 1942 265 700
consumergoods.uk@intertek.com
intertek.com

FLAMMABILITY TEST REPORT

Report No.: LEI20060411A Date Received: 08/06/20 Date Tested: 10/06/20 Date Issued: 10/06/20

Company Name & Address:

Contact Name:

Sample Details

Order No.: P30520
Description: Decorative Velvet blackout fabric
Article:
Ref. / Style No.: Not stated
Colour: Blush
Quality: 6742/279
Colour: Not stated
Supplier: Not stated
Batch No.: C58692
End Use: Curtaining
Quoted Fibre Composition: 100 Polyester with Acrylic Back coating
Retailer: Not stated
Buying Division: Not stated
Sample Description: Pink coloured woven fabric with pile and white coloured backing

| Test Method | Pre Treatment | Performance Requirement | Result |
|--|--|---|--------|
| IMO FTP Code (2010) Annex 1, Part 7: Test for Vertically Orientated Support Textiles and Films | None – The scope states that “fabrics which are not inherently flame resistant should be exposed to cleaning or exposure procedures” | IMO FTP Code (2010) Annex 1, Part 7, Clause 3 | PASS |

Note: The fabric supplied was tested with no pre-treatments at the request of the customer.
Please note: The testing was carried out in the ISO 6941 environment

.....
STEVEN OWEN
(Technical & Operational
Excellence Manager)


.....
ANDREW HALLETT
(Flammability Team Leader)

.....
CAROLE SPOWART
(Flammability
Administrator)

.....
GREGORY JAMES
(Flammability Technician)

Report No.: LEI20060411A Page 1 of 2

ITS Testing Services (UK) Ltd
Registered in England No. 1408264. Registered Office: Academy Place, 1-9 Brook Street, Brentwood, Essex, CM14 5NQ



 United Kingdom

 +44 1422 833835

 uksales@jcjoel.com

 United Arab Emirates

 +971 4 884 7801

 menasales@jcjoel.com

www.jcjoel.com

Fire Test Certificate - Specimen

Fabric: Embrace

Type: IMO

J&C Joel 
Inspiration in every performance

intertek
Total Quality. Assured.

Intertek
The Warehouse
Brewery Lane
Leigh WN7 2RJ
UK

Tel +44 1942 265 700
consumergoods.uk@intertek.com
intertek.com

FLAMMABILITY TEST REPORT

Additional Information (Annex)

Name and Address of the Sponsor: Not Stated
Name and Address of the Manufacturer/Supplier (if known):
Type of Furniture: Not Stated
Fabric Details - Weave/Density/Yarn count/thickness(mm)/mass(g/m²) Colour & Tone: Not Stated
Fire Retardant Treatment: No

Test Specification

Test Method: IMO FTP Code (2010) Annex 1, Part 7
Ignition Source: 40mm high Propane gas flame
Ignition Type: Face ignition (as determined by the pre-test)
Flame Application Time: 15 seconds (as determined by the pre-test)
Sample Size: 220 x 170mm
Side Tested: Face

Pre-treatment / Durability Procedure

None - At the request of the customer.

Conditioning

Prior to Testing: At least 24 hours in an atmosphere having a temperature of 20±5°C and relative humidity of 65±5%
At Time of Testing: Temperature between 15°C & 30°C. Relative humidity between 20% & 60%

Test Results

Report of tests carried out in accordance IMO FTP Code (2010) Annex 1, Part 7.

"The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use."

| Sample No./ Direction | Duration of flaming (Secs) | Duration of afterglow (Secs) | Flaming debris | Flame to edge | Hole to edge | Maximum damaged length (mm) | | Average Damage Length (mm) |
|-----------------------|----------------------------|------------------------------|----------------|---------------|--------------|-----------------------------|----------|----------------------------|
| | | | | | | Horizontal | Vertical | |
| 1. Length ↑ | 0.0 | 0.0 | No | No | No | 22 | 113 | 105.0 |
| 2. Length ↓ | 0.0 | 0.0 | No | No | No | 27 | 132 | |
| 3. Length ↑ | 0.0 | 0.0 | No | No | No | 23 | 125 | |
| 4. Length ↓ | 0.0 | 0.0 | No | No | No | 22 | 130 | |
| 5. Length ↑ | 0.0 | 0.0 | No | No | No | 24 | 125 | |
| 6. Width → | 0.0 | 0.0 | No | No | No | 24 | 125 | 103.6 |
| 7. Width ← | 0.0 | 0.0 | No | No | No | 23 | 110 | |
| 8. Width → | 0.0 | 0.0 | No | No | No | 23 | 125 | |
| 9. Width ← | 0.0 | 0.0 | No | No | No | 22 | 130 | |
| 10. Width → | 0.0 | 0.0 | No | No | No | 23 | 98 | |

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or willful misconduct.

Report No.: LEI20060411A Page 2 of 2

ITS Testing Services (UK) Ltd
Registered in England No. 1408264. Registered Office: Academy Place, 1-9 Brook Street, Brentwood, Essex, CM14 5NQ



 United Kingdom

 +44 1422 833835

 uksales@jcjoel.com

 United Arab Emirates

 +971 4 884 7801

 menasales@jcjoel.com

www.jcjoel.com