

Fire Test Certificate

Fabric: Novello Crushed Velvet

Type: M1

J&C Joel
Inspiration in every performance

SGS

TEST REPORT

No.: AJFTS26005824R01_EN

Date: Jul 28, 2026

Page 1 of 5

J&C JOEL LTD

Corporation Street, Sowerby Bridge, HX6 2QQ, UK

Sample Description : IFR Crushed Velvet

Style/Item No. : /

The above sample(s) data and information was / were submitted and identified on behalf of the client. SGS is not responsible for the authenticity, integrity and results of the data and information and / or the validity of the conclusion arising therefrom. Results apply to the sample as received.

Sample Receiving Date : Jul 20, 2026

Testing Period : Jul 20, 2026 to Jul 24, 2026

Test Required : NF P 92-507:2004 Fire safety-building-interior fitting materials-Classification according to their reaction to fire.

Test result(s) : See attached sheet

Conclusion : Classification: M1

Signed for and on behalf of
SGS-CSTC Standards Technical Services Co., Ltd Anji Branch

Eva

Eva Zhang
Approved signatory

Scan to see the report



AJFTS26005824R01
Verification:
check.sgschina.com.cn



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing (inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

No. 301, Sunlight Road, 2 Block, Sunlight Industry Zone, Anji County, Zhejiang Province, China 313300 t (86-572) 5018825 f (86-572) 5018829 www.sgsgroup.com.cn
中国·浙江·安吉县阳光工业园区二区阳光大道301号 邮编: 313300 t (86-572) 5018825 f (86-572) 5018829 sgs.china@sgs.com

Member of the SGS Group (SGS SA)

United Kingdom

+44 1422 833835

uksales@jcjoel.com

United Arab Emirates

+971 4 884 7801

menasales@jcjoel.com

www.jcjoel.com

Fire Test Certificate

Fabric: Novello Crushed Velvet

Type: M1

J&C Joel
Inspiration in every performance

SGS

TEST REPORT

No.: AJFTS26005824R01_EN

Date: Jul 28, 2026

Page 2 of 5

I. Test conducted

This test was conducted according to NF P 92-507:2004 Fire safety - building-interior fitting materials - Classification according to their reaction, and the test methods as following:

1. NF P 92-503:1995 Safety against fire - Building materials - Reaction to fire tests Electrical burner test used for flexible materials.
2. NF P 92-504:1995 Safety against fire - Building materials - Reaction to fire tests - Flame persistence test and speed of the spread of flame.

II. Sample details

Sample description	Fabric
Color	Blue
Area density	328 g/m ²
Specimen size	600 mm × 180 mm (NF P 92-503) 460 mm × 230 mm (NF P 92-504)

III. Conditioning

Prior to testing, the sample was conditioned in an atmosphere having a temperature of 23±2°C and a relative humidity of 50±5% for 7 days or until constant mass is obtained.

IV. Test results

i) NF P 92-503:1995 Electrical burner test

Face, Length

After testing, the following details are noted	Specimen No.				
	1	2	3	4	Average
Hole (Yes/No)	Yes	Yes	Yes	Yes	
Applied time (s)	20	20	20	20	
Max. afterflame time after withdrawal the pilot flame (s)	0	0	0	0	0
Afterglow time (s)	0	0	0	0	0
Flaming molten droplets (Yes/No)	No	No	No	No	
Non-flaming molten droplets (Yes/No)	No	No	No	No	
Flaming debris (Yes/No)	No	No	No	No	
Non-flaming debris (Yes/No)	No	No	No	No	
White-hot spots with propagation effects (Yes/No)	No	No	No	No	



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/terms-and-conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained herein reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing (inspection report & certificate), please contact us at telephone: (86-755) 8397 1443, or email: CN.Doccheck@sgs.com

No. 301, Sunlight Road, 2 Block, Sunlight Industry Zone, Anji County, Zhejiang Province, China 313300 t: (86-572) 5018825 f: (86-572) 5018829 www.sgs.com.cn
中国·浙江·安吉县阳光工业园二区阳光大道301号 邮编: 313300 t: (86-572) 5018825 f: (86-572) 5018829 sgs.china@sgs.com

Member of the SGS Group (SGS SA)



United Kingdom



+44 1422 833835



uksales@jcjoel.com



United Arab Emirates



+971 4 884 7801



menasales@jcjoel.com

www.jcjoel.com

Fire Test Certificate

Fabric: Novello Crushed Velvet

Type: M1

J&C Joel
Inspiration in every performance

SGS

TEST REPORT

No.: AJFTS26005824R01_EN

Date: Jul 28, 2026

Page 3 of 5

After testing, the following details are noted	Specimen No.				
	1	2	3	4	Average
Max. destruction length from the lower edge (mm)	125	121	128	126	125.0
Max. width of the destroyed zones between 450mm and 600mm from the test piece lower edge (mm)	0	0	0	0	0

ii) NF P 92-504:1995 Flame persistence test

Face, Length

Ignition time	After-flame time (s)	Flaming Drops (Yes/No)	Non-flaming Drops (Yes/No)	Ignition times	After-flame time (s)	Flaming Drops (Yes/No)	Non-flaming Drops (Yes/No)
1	0	No	No	16	0	No	No
2	0	No	No	17	0	No	No
3	0	No	No	18	0	No	No
4	0	No	No	19	0	No	No
5	0	No	No	20	0	No	No
6	0	No	No	21	0	No	No
7	0	No	No	22	0	No	No
8	0	No	No	23	0	No	No
9	0	No	No	24	0	No	No
10	0	No	No	25	0	No	No
11	0	No	No	26	0	No	No
12	0	No	No	27	0	No	No
13	0	No	No	28	0	No	No
14	0	No	No	29	0	No	No
15	0	No	No	30	0	No	No

Number of tested specimens: 4



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained herein reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing/inspection report & certificate, please contact us at telephone: (86-755) 8397 1443, or email: CN.Doccheck@sgs.com

No. 301, Sunlight Road, 2 Block, Sunlight Industry Zone, Anji County, Zhejiang Province, China 313300 t: (86-572) 5018825 f: (86-572) 5018829 www.sgs.com
中国·浙江·安吉县阳光工业园二区阳光大道301号 邮编: 313300 t: (86-572) 5018825 f: (86-572) 5018829 sgs.china@sgs.com

Member of the SGS Group (SGS SA)

United Kingdom

+44 1422 833835

uksales@jcjoel.com

United Arab Emirates

+971 4 884 7801

menasales@jcjoel.com

www.jcjoel.com

Fire Test Certificate

Fabric: Novello Crushed Velvet

Type: M1

J&C Joel
Inspiration in every performance

SGS

TEST REPORT

No.: AJFTS26005824R01_EN

Date: Jul 28, 2026

Page 4 of 5

Annex I, Requirements

Table 1 Resume of classification for flexible materials which thickness no more than 5mm

Test Items	Criteria of classification				
<u>Test for hot melt materials</u>		Not ignite the wadding	Not ignite the wadding	Ignite the wadding	Ignite the wadding
<u>Electrical Burner Test</u> ^{a)}	No drops	Non-flaming molten droplets	Flaming drops or debris	Non-flaming molten droplets	Flaming drops or debris
Inflammation ≤ 5s	M1	M1	M2	M4	M4
Inflammation > 5s and Average destroyed length < 350 mm	M2	M2	M3	M4	M4
Inflammation > 5s and Average destroyed width < 90 mm between the 450 mm and 600 mm in length	M3	M3	M4	M4	M4
<u>Flame Spread Test</u> (flame spread < 2 mm/s)			M4	M4	M4
^{a)} If the materials presented a particular behaviour, the classification also need to refer to Table 3. The details of classification M0 refer to clause 3.3 of NF P 92-507:2004.					



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained herein reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8397 1443, or email: CN.Doccheck@sgs.com
No. 301, Sunlight Road, 2 Block, Sunlight Industry Zone, Anji County, Zhejiang Province, China 313300 t (86-572) 5010825 f (86-572) 5010829 www.sgs.com.cn
中国·浙江·安吉县阳光工业园二区阳光大道301号 邮编: 313300 t (86-572) 5010825 f (86-572) 5010829 sgs.china@sgs.com

Member of the SGS Group (SGS SA)



United Kingdom



+44 1422 833835



uksales@jcjoel.com



United Arab Emirates



+971 4 884 7801



menasales@jcjoel.com

www.jcjoel.com

Fire Test Certificate

Fabric: Novello Crushed Velvet

Type: M1

J&C Joel
Inspiration in every performance

SGS

TEST REPORT

No.: AJFTS26005824R01_EN

Date: Jul 28, 2026


Page 5 of 5

Table 3 Resume of classification for the materials presented a particular behaviour

Test Items	Criteria of classification				
		Not ignite the wadding	Not ignite the wadding	Ignite the wadding	Ignite the wadding
<u>Test for hot melt materials</u>					
<u>Flame Persistence Test</u>	No drops	Non-flaming molten drops	Flaming drops or debris	Non-flaming molten drops	Flaming drops or debris
Flame persistence time ≤ 2s	M1	M1	M2	M4	M4
Flame persistence time ≤ 5s	M2	M2	M3	M4	M4
Flame persistence time > 5s and Flame Spread < 2 mm/s	M3	M3	M4	M4	M4

Statement: This declaration of conformity is only based on the result of this laboratory activity, the impact of the uncertainty of the results was not included.

Photo Appendix:



SGS authenticate the photo on original report only

End of Report



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained herein reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing (inspection report & certificate, please contact us at telephone: (86-755) 8387 1443, or email: CN.Doccheck@sgs.com

No. 301, Sunlight Road, 2 Block, Sunlight Industry Zone, Anji County, Zhejiang Province, China 313300 t (86-572) 5018825 f (86-572) 5018829 www.sgs.com.cn
中国·浙江·安吉县阳光工业园二区阳光大道301号 邮编: 313300 t (86-572) 5018825 f (86-572) 5018829 sgs.china@sgs.com

Member of the SGS Group (SGS SA)



United Kingdom



+44 1422 833835



uksales@jcjoel.com



United Arab Emirates



+971 4 884 7801



menasales@jcjoel.com

www.jcjoel.com